TRAP ROCK INDUSTRIES, LLC

Quality Control Division Kingston, NJ

Mailing Address: Laurel Ave., Kingston, NJ 08528 PHONE 609-924-0300 FAX 609-252-8940

Analysis of			TYPCIAL 1/4" Trap Rock							_material	
DATE TESTED 2025		LOCATION OF SAMPLE				Typical Gradation				-	
SIEVE SIZE			Spec.	1/4"	Spec.		Spec.		Spec.		Spec.
4"	100. mm										
3 1/2"	87.5 mm										
3"	75.0 mm										
2 1/2"	62.5 mm										
2"	50.0 mm										
1 1/2"	37.5 mm										
1"	25.0 mm										
3/4"	19.0 mm										
1/2"	12.5 mm										
3/8"	9.5 mm			100.0							
# 4	4.75 mm			89.5							
# 8	2.36 mm			11.7							
# 10	2.00 mm			6.1							
# 16	1.18 mm			1.5							
# 30	.600 um			0.5							
# 40	.425 um										
# 50	.300 um			0.3							
# 80	.180 um										
# 100	.150 um			0.2							
# 200	.075 um			0.1							
MOISTURES											
Distribution:		Remarks: unit weight lbs per cubic ft - loose & rodded 95.5 / 100.2 BY									

THIS TECHNICAL SERVICE IS PROVIDED IN CONJUNCTION WITH A PROGRESSIVE RESEARCH AND CONTROL PROGRAM DESIGNED TO ASSURE OUR CLIENTS OF A MORE UNIFORM, HIGHER QUALITY PRODUCT.

TRAP ROCK INDUSTRIES