## TRAP ROCK INDUSTRIES, LLC.

Quality Control Division Kingston, NJ Mailing Address: Laurel Ave., Kingston, NJ 08528 PHONE 609-924-0300 FAX 609-252-8940

Analysis of

**KINGSTON AASHTO** 

material

DATE TESTED

2025

LOCATION OF SAMPLE TYPICAL GRADATION

#4, 1 1/2"

SIEVE SIZE		# 4	NJDOT Spec.		Spec.	Spec.	Spec.	Spec.
4"	100. mm							
3 1/2"	87.5 mm							
3"	75.0 mm							
2 1/2"	62.5 mm							
2"	50.0 mm	100.0	100					
1 1/2"	37.5 mm	93.5	90 / 100					
1"	25.0 mm	35.0	20 / 55					
3/4"	19.0 mm	5.5	0 / 15					
1/2"	12.5 mm	4.0						
3/8"	9.5 mm	3.0	0/5					
# 4	4.75 mm							
# 8	2.36 mm							
# 10	2.00 mm							
# 16	1.18 mm							
# 30	.600 um							
# 40	.425 um							
# 50	.300 um							
# 80	.180 um							
# 100	.150 um							
# 200	.075 um							
MOISTURES								

**Distribution:** 

Remarks:

BY

TRAP ROCK INDUSTRIES

THIS TECHNICAL SERVICE IS PROVIDED IN CONJUNCTION WITH A PROGRESSIVE RESEARCH AND CONTROL PROGRAM DESIGNED TO ASSURE OUR CLIENTS OF A MORE UNIFORM, HIGHER QUALITY PRODUCT.