

Trap Rock Industries, LLC.
 Quality Control Division
 Phone 609-924-0300
 Fax 609-252-8940

Product: KINGSTON 1 1/2" Blend

Location: STOCKPILE

Date: 2025

AASHTO T-99 METHOD C WITH REPLACEMENT

Max. Dry Density - lbs/ft³: 148.1
Optimal Moisture % : 8.9

Gradation

SIZE	% PASSING
1-1/2" (37.5mm)	100
3/4" (19.0mm)	79.5
#4 (4.75mm)	36.8
#50 (300um)	13.6
#200 (775um)	7.2

Moisture %	4%	6%	8%	10%	12%			
Dry Density	111.3	134.3	147.3	146.8	143.5			

