

# TRAP ROCK INDUSTRIES, LLC

Quality Control Division

Kingston, NJ

Mailing Address: Laurel Ave., Kingston, NJ 08528

PHONE 609-924-0300 FAX 609-252-8940

Analysis of KINGSTON AASHTO # 3 material

DATE TESTED 2025 LOCATION OF SAMPLE TYPICAL GRADATION

SIEVE SIZE		Spec.		Spec.		Spec.		Spec.		Spec.	
4"	100. mm										
3 1/2"	87.5 mm										
3"	75.0 mm										
2 1/2"	62.5 mm	100.0	100								
2"	50.0 mm	94.0	90 / 100								
1 1/2"	37.5 mm	57.5	35 / 70								
1"	25.0 mm	12.5	0 / 15								
3/4"	19.0 mm	2.0									
1/2"	12.5 mm	0.8	0 / 5								
3/8"	9.5 mm										
# 4	4.75 mm										
# 8	2.36 mm										
# 10	2.00 mm										
# 16	1.18 mm										
# 30	.600 um										
# 40	.425 um										
# 50	.300 um										
# 80	.180 um										
# 100	.150 um										
# 200	.075 um										
MOISTURES											

Distribution:  
LAB

Remarks:

BY

TRAP ROCK INDUSTRIES

THIS TECHNICAL SERVICE IS PROVIDED IN CONJUNCTION WITH A PROGRESSIVE RESEARCH AND CONTROL PROGRAM DESIGNED TO ASSURE OUR CLIENTS OF A MORE UNIFORM, HIGHER QUALITY PRODUCT.