TRAP ROCK INDUSTRIES, LLC.

Quality Control Division Kingston, NJ

Mailing Address: Laurel Ave., Kingston, NJ 08528 PHONE 609-924-0300 FAX 609-252-8940

Analysis of			KINGSTON AASHTO # 57 ARGILLITE material				_material
DATE TESTED		2025	_	LOCATION OF SAME	PLE <u>TY</u> I	PICAL GRADA	TION
SIEVE SIZE		# 57	Spec.	Spec.	Spec.	Spec.	Spec.
4"	100. mm						
3 1/2"	87.5 mm						
3"	75.0 mm						
2 1/2"	62.5 mm						
2"	50.0 mm						
1 1/2"	37.5 mm	100.0	100				
1"	25.0 mm	100.0	95 / 100				
3/4"	19.0 mm	84.3					
1/2"	12.5 mm	36.8	25 / 60				
3/8"	9.5 mm	14.7					
# 4	4.75 mm	2.2	0 / 10				
# 8	2.36 mm	1.1	0/5				
# 10	2.00 mm						
# 16	1.18 mm						
# 30	.600 um						
# 40	.425 um						
# 50	.300 um						
# 80	.180 um						
# 100	.150 um						
# 200	.075 um						
MOISTURES							
Distribution:		Remarks: unit weight lbs per cubic ft - loose & rodded 94.2 / 99.4					

THIS TECHNICAL SERVICE IS PROVIDED IN CONJUNCTION WITH A PROGRESSIVE RESEARCH AND CONTROL PROGRAM DESIGNED TO ASSURE OUR CLIENTS OF A MORE UNIFORM, HIGHER QUALITY PRODUCT.

TRAP ROCK INDUSTRIES

BY