

Trap Rock Industries, LLC.

Quality Control Division

Phone 609-924-0300

Fax 609-252-8940

Product: Kingston Argillite DGABC

Location: STOCKPILE

Date: 2025 AASHTO T-99 METHOD C WITH REPLACEMENT

Max. Dry Density - lbs/ft<sup>3</sup>: 136.1

Optimal Moisture % : 8.7

SIZE	Gradation	% PASSING	NJDOT Spec.
1 1/2" (37.5mm)		100	100%
3/4" (19.0mm)		83.5	55-90%
1/2" ( 12.5mm )		76.2	
#4 (4.75mm)		42.1	25-50%
#50 (300um)		16.1	5-20%
#200 (775um)		7.8	3-10%

Moisture %	4%	6%	8%	10%	12%			
Dry Density	103.5	126.6	135.6	135.1	132.9			

