## TRAP ROCK INDUSTRIES, LLC.

Quality Control Division Kingston, NJ

Mailing Address: Laurel Ave., Kingston, NJ 08528 PHONE 609-924-0300 FAX 609-252-8940

Analysis of			KINGSTON AASHTO # 10- ARGILLITE							material	
DATE TESTED 2025		2025	_ LOCATION OF SAMPLE				TYPICAL GRADATION				-
SIEVE SIZE		# 10	NJDO1	Γ Spec.	Spec.		Spec.		Spec.		Spec.
4"	100. mm			•					•		
3 1/2"	87.5 mm										
3"	75.0 mm										
2 1/2"	62.5 mm										
2"	50.0 mm										
1 1/2"	37.5 mm										
1"	25.0 mm										
3/4"	19.0 mm										
1/2"	12.5 mm										
3/8"	9.5 mm	100.0	100								
# 4	4.75 mm	99.5	85 / 100								
# 8	2.36 mm	78.1									
# 10	2.00 mm										
# 16	1.18 mm	48.3									
# 30	.600 um	30.2									
# 40	.425 um										
# 50	.300 um	18.5									
# 80	.180 um										
# 100	.150 um	12.4	10 / 30								
# 200	.075 um	8.4									
MOISTURES											
Distribution:		Remarks:									
			unit weig	int ibs per c	cubic ft - loos	e & rodded	İ				

92.2 / 100.9

THIS TECHNICAL SERVICE IS PROVIDED IN CONJUNCTION WITH A PROGRESSIVE RESEARCH AND CONTROL PROGRAM DESIGNED TO ASSURE OUR CLIENTS OF A MORE UNIFORM, HIGHER QUALITY PRODUCT.

TRAP ROCK INDUSTRIES

BY