

# TRAP ROCK INDUSTRIES, INC.

Quality Control Division  
Kingston, NJ  
Mailing Address: Laurel Ave., Kingston, NJ 08528  
PHONE 609-924-0300 FAX 609-252-8940

Analysis of KINGSTON WASHED SEPTIC STONE material

DATE TESTED 2025 LOCATION OF SAMPLE TYPICAL GRADATION

SIEVE SIZE			Spec.	SEPTIC	Spec.		Spec.		Spec.		Spec.
4"	100. mm			STONE							
3 1/2"	87.5 mm										
3"	75.0 mm										
2 1/2"	62.5 mm										
2"	50.0 mm			100.0							
1 1/2"	37.5 mm			92.0							
1"	25.0 mm			27.0							
3/4"	19.0 mm			2.0							
1/2"	12.5 mm			1.0							
3/8"	9.5 mm			0.1							
# 4	4.75 mm										
# 8	2.36 mm										
# 10	2.00 mm										
# 16	1.18 mm										
# 30	.600 um										
# 40	.425 um										
# 50	.300 um										
# 80	.180 um										
# 100	.150 um										
# 200	.075 um										
MOISTURES											

Distribution:

Remarks:

BY

TRAP ROCK INDUSTRIES

THIS TECHNICAL SERVICE IS PROVIDED IN CONJUNCTION WITH A PROGRESSIVE RESEARCH AND CONTROL PROGRAM DESIGNED TO ASSURE OUR CLIENTS OF A MORE UNIFORM, HIGHER QUALITY PRODUCT.