

TRAP ROCK INDUSTRIES, LLC

Quality Control Division
 Kingston, NJ
 Mailing Address: Laurel Ave., Kingston, NJ 08528
 PHONE 609-924-0300 FAX 609-252-8940

Analysis of FINISH STONE material

DATE TESTED 2026 LOCATION OF SAMPLE Typical Gradation

SIEVE SIZE			Spec.		Spec.		Spec.		Spec.		Spec.
4"	100. mm										
3 1/2"	87.5 mm										
3"	75.0 mm										
2 1/2"	62.5 mm										
2"	50.0 mm										
1 1/2"	37.5 mm										
1"	25.0 mm										
3/4"	19.0 mm										
1/2"	12.5 mm	100.0									
3/8"	9.5 mm	97.0									
# 4	4.75 mm	60.8									
# 8	2.36 mm	41.6									
# 10	2.00 mm										
# 16	1.18 mm	28.0									
# 30	.600 um	19.0									
# 40	.425 um										
# 50	.300 um	12.0									
# 80	.180 um										
# 100	.150 um	9.0									
# 200	.075 um	5.5									
MOISTURES											

Distribution:
LAB

Remarks:

BY TRAP ROCK INDUSTRIES

THIS TECHNICAL SERVICE IS PROVIDED IN CONJUNCTION WITH A PROGRESSIVE RESEARCH AND CONTROL PROGRAM DESIGNED TO ASSURE OUR CLIENTS OF A MORE UNIFORM, HIGHER QUALITY PRODUCT.