



Detailed Quality Summary Report

Plant KINGSTON
 Product ARGILLITE DGABC
 Specification NJDOT DGABC
 Period 1/1/26 - PRESENT

| Sieve / Test | Results | Specification |
|------------------|---------|---------------|
| 1 1/2" (37.5mm) | 100.0 | 100 |
| 1" (25mm) | 90.7 | |
| 3/4" (19mm) | 83.5 | 55 / 90 |
| 3/8" (9.5mm) | 49.7 | |
| #4 (4.75mm) | 42.1 | 25 / 50 |
| #8 (2.36mm) | 36.8 | |
| #50 (.300um) | 16.1 | 5 / 20 |
| #200 (.075 um) | 7.8 | 3 / 10 |

Other Test Results

AASHTO T-99 Method C
Max Dry Density 136.1 lbs. / cubic ft
Optimal Moisture Percentage 8.7

