



Detailed Quality Summary Report

Plant KINGSTON
Product KINGSTON SUBBASE
Specification NJDOT - RCA DGABC
Period 1/1/26 - PRESENT

Sieve / Test	Results	Specification
1 1/2" (37.5mm)	100.0	100
1" (25mm)	95.8	
3/4" (19mm)	85.3	55 / 90
3/8" (9.5mm)	51.2	
#4 (4.75mm)	43.8	25 / 50
#8 (2.36mm)	36.9	
#50 (.300um)	12.9	5 / 20
#200 (.075 um)	6.6	3 / 10

Other Test Results

AASHTO T-99 Method C
Max Dry Density 121.8 lbs. / cubic ft
Optimal Moisture Percentage 12.2

