



Detailed Quality Summary Report

Plant KINGSTON
Product KINGSTON UTILITY SAND
Specification
Period 1/1/26 - PRESENT

Sieve / Test	Results	Specification
3/8" (9.5mm)	100.0	
#4 (4.75mm)	100.0	
#8 (2.36mm)	100.0	
#50 (.300um)	100.0	
#100 (.150um)	100.0	
#200 (.075 um)	91.0	

Other Test Results

AASHTO T-99 Method C
Max Dry Density 105.4 lbs. / cubic ft
Optimal Moisture Percentage 28.4

